

Material Characteristics

Ni-Zn Material

Material			L-81	
Initial permeability	μ_{iac}			350 ±25%
Relative loss factor	$\tan\delta/\mu_{iac}$	$\times 10^{-6}$	25°C	25 (1.0MHz)
Saturation flux density (1194A/m)	Bs	mT	25°C	330
Remanence	Br	mT	25°C	80
Coercivity	Hc	A/m	25°C	48
Relative temp. factor (20°C~60°C)	$\alpha\mu r$	$\times 10^{-6}/^\circ\text{C}$		5~10
Curie Temperature	Tc	°C		>170
Density	d	kg/m ³		5.0×10 ³
Resistivity	ρ	MΩ·m	25°C	>10

Note : 1) Typical values
 2) The values were obtained with toroidal cores(30X8-20H) at room temperature unless indicated otherwise

